

18-15-00

PTO/SB/05 (1/98)

Please type a plus sign (+) inside this box

Approved for use through 09/30/2000. OMB 0651-0032

Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

UTILITY PATENT APPLICATION TRANSMITTAL

Attorney Docket No. 3636.1US (97-1349.1)First Inventor or Application Identifier Chad A. Cobbley

(Only for new nonprovisional applications under 37 CFR 1.53(b)) Express Mail Label No.

METHOD OF ATTACHING SOLDER BALLS TO BGA PACKAGE UTILIZING A TOOL TO PICK AND DIP THE SOLDER BALL IN FLUX EL638963288US

| Al | PPLICATION ELEMENTS | Assistant Commissi ADDRESS TO: Box Patent Applicat | | | |
|--------------|---|--|--------------------------------|--|--|
| See MPEP cha | apter 600 concerning utility patent application contents. | Washington, DC 20 | | | |
| | ee Transmittal Form (e.g., PTO/SB/17) spirit an original, and a duplicate for fee processing) | 6. Microfiche Computer Program (| | | |
| | ecification [Total Pages 17] eferred arrangement set forth below) | Nucleotide and/or Amino Acid Sequer (if applicable, all necessary) | ce Submission | | |
| | Descriptive title of the Invention | a. Computer Readable Co | | | |
| | cross References to Related Applications statement Regarding Fed sponsored R & D | b. Paper Copy (identical to | computer copy) | | |
| | Reference to Microfiche Appendix | c. Statement verifying ider | tity of above conies | | |
| - B | ackground of the Invention | o otatomork vorthying tool | inty of above copies | | |
| - B | rief Summary of the Invention | ACCOMPANYING APPLICATION | ACCOMPANYING APPLICATION PARTS | | |
| - B | rief Description of the Drawings (if filed) | | | | |
| | Detailed Description | 8. Assignment Papers (cover shee | t & document(s)) | | |
| 1 | claim(s) bstract of the Disclosure | 9. 37 C.F.R.§3.73(b) Statement (when there is an assignee) | Power of Attorney | | |
| | awing(s) (35 U.S.C. 113) [Total Sheets 10] | 10. English Translation Document (| if applicable) | | |
| 4. Oath or D | Declaration [Total Pages 2] | 11. X Information Disclosure Statement (IDS)/PTO-1449 | Copies of IDS Citations | | |
| а. Г | Newly executed (original or copy) | 12. Preliminary Amendment | | | |
| b. [| Copy from a prior application (37 C.F.R. § 1.6 (for continuation/divisional with Box 17 completed) | (d)) 13. X Return Receipt Postcard (MPEF | | | |
| | [Note Box 5 below] DELETION OF INVENTOR(S) | * Small Entity | filed in prior application, | | |
| | i. Signed statement attached deleting | | proper and desired | | |
| | inventor(s) named in the prior application | Certified Copy of Priority Docum | nent(s) | | |
| 5. X Incor | see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b) rporation By Reference (useable if Box 4b is checked) | (if foreign priority is claimed) | . , | | |
| The | entire disclosure of the prior application, from which | | | | |
| | of the oath or declaration is supplied under Box 4 sidered to be part of the disclosure of the accompar | | ov amall artifu face avaant | | |
| | ication and is hereby incorporated by reference the | | | | |
| | NTINUING APPLICATION, check appropriate box, and | | inary amendment: | | |
| | ontinuation X Divisional Continuation-in-par | (CIP) of prior application No [.] 09 <i>[</i> 1 | L67 , 763 | | |
| Prior ap | oplication information: Examıner Z. Pittman | Group / Art Unit: 1725 | | | |
| | 18. CORRESPON | DENCE ADDRESS | | | |
| | | | | | |
| Custom | ner Number or Bar Code Label | • | lence address below | | |
| | ; (Insert Customer No. or) | ftach bar code label here): | | | |
| Name | James R. Duzan | | | | |
| | Trask Britt | | | | |
| Address | P.O. Box 2550 | | | | |
| City | Salt Lake City State | Utah Zip Code 8411 | 10 | | |
| Country | U.S.A. Telephone | (801) 532-1922 | | | |
| Name (| | Posiotration No. (44 | | | |
| <u> </u> | values N. Duzan | | 393 | | |
| Signatur | · James R. Duga | Date 08/ | 14/2000 | | |

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

| NOTICE | OF EXPRESS MAILING |
|----------------------------|------------------------------|
| Express Mail Mailing Label | Number: <u>EL638963288US</u> |
| Date of Deposit with USPS | August 14, 2000 |
| Person making Deposit: | Jared S. Turner |

APPLICATION FOR LETTERS PATENT

for

METHOD OF ATTACHING SOLDER BALLS TO BGA PACKAGE UTILIZING A TOOL TO PICK AND DIP THE SOLDER BALL IN FLUX

Inventors: Chad A. Cobbley Michael B. Ball Marjorie L. Waddel

Attorney: James R. Duzan Registration No. 28,393 TRASK BRITT P.O. Box 2550 Salt Lake City, Utah 84110 (801) 532-1922

METHOD OF ATTACHING SOLDER BALLS TO BGA PACKAGE UTILIZING A TOOL TO PICK AND DIP THE SOLDER BALL IN FLUX

CROSS-REFERENCE TO RELATED APPLICATION

This application is a divisional of application Serial No. 09/167,763, filed October 7, 1998, pending.

BACKGROUND OF THE INVENTION

10

15

5

<u>Field of the Invention</u>: This invention relates generally to semiconductor device manufacturing. More particularly, the instant invention pertains to methods and apparatus for handling solder balls in forming ball grid arrays (BGA's).

State of the Art: Integrated circuit semiconductor devices (IC's) are small electronic circuits formed on the surface of a wafer of semiconductor material such as silicon. The IC's are fabricated in plurality in wafer form and tested by a probe to determine electronic characteristics applicable to the intended use of the IC's. The wafer is then subdivided into discrete IC chips or dice, and then further tested and assembled for customer use through various well-known individual die IC testing and packaging techniques, including lead frame packaging, Chip-On-Board (COB) packaging, and flip-chip packaging (FCP). Depending upon the die and wafer sizes, each wafer is divided into a few dice or as many as several hundred or more than one thousand discrete dice.

20

Interconnection of discrete semiconductor packages onto a substrate such as a printed circuit board (PCB) is often accomplished with solder preforms having spherical, near-spherical or other shapes. In a process using a ball-grid-array (BGA), spherical or near-spherical solder balls are attached to prefluxed metallized locations on a workpiece such as a circuit board or a semiconductor device. The workpiece is then heated, typically at temperatures of 183°C or greater, to reflow the solder balls, and the solder balls become attached to the metallized locations during subsequent cooling. A semiconductor package or circuit board having a corresponding but reversed pattern of connection sites

25

10

15

20

25

may then be aligned with the BGA and bonded to it by controlled heating in a reflow furnace.

The use of flip-chip technology with solder bumps has numerous advantages for interconnection. Flip-chip technology provides improved electrical performance for high frequency applications such as mainframes and computer workstations. Flip-chip interconnections are of very small size. In addition, easier thermal management and reduced susceptibility to interference caused by a variety of sources are inherent.

Surface mount technology (SMT) using solder "bump" interconnects eliminates the outer package leads level of interconnection, significantly reducing the cost.

Solder bumps may be formed on a workpiece by processes of evaporation, electroplating, stencil printing and serial methods. Each of these processes has particular limitations. Illustrated in United States Patent 5,672,542 of Schwiebert et al. is an example of a modified stencil printing process.

In United States Patent 3,716,907 of Anderson, the use of germanium hemispheres as conductive contacts is disclosed.

Relative to other types of interconnections, the use of solder preforms, in particular spherical or near-spherical balls, has proven to have significant advantages. One advantage is that while the solder balls are formed with significant ball-to-ball size differences, they may be easily classified by size prior to application to a workpiece. Thus, a uniform size of solder balls may be used within a ball-grid-array.

Various methods have been used for aligning, placing, retaining and fixing solder balls on an array of sites on a workpiece.

In United States Patent 5,620,927 of Lee, a template with an array of through-holes is placed on the workpiece and solder balls are introduced into the holes by rolling the solder balls across the workpiece surface. The apparatus may be installed on a tilt table to encourage filling of all holes. In United States Patent 4,871,110 of Fukasawa et al., a template having an array of holes is placed on a ball holder with a like array of smaller holes to which vacuum is applied and over which solder balls are rolled. After the array is filled with solder balls, the template and ball holder with balls are removed and the

10

15

20

25

exposed ends of the balls attached to a substrate by e.g. reflow. The template and ball holder are then pulled from the substrate, leaving a ball-grid-array ready for attachment to another substrate or workpiece.

As shown in United States Patent 3,719,981, an array of solder balls is arranged on the tacky surface of a pressure sensitive (PS) tape for alignment through a template to solder bumps on a wafer. After thermal reflow, the template and tape are removed.

The use of a template for forming solder bumps or "balls" on a workpiece from flux and solder pieces is disclosed in United States Patent 5,492,266 of Hoebener et al.

In United States Patent 5,431,332 of Kirby et al., a template is placed over the bond pads of a substrate, solder balls are poured over the template, and an air knife "sweeps" the surface free of excess solder balls.

The use of a ball pickup tool with an array of vacuum suction ball retainers to pull up balls from an underlying reservoir is disclosed in United States Patent 5,088,639 of Gondotra et al., United States Patent 5,284,287 of Wilson et al., United States Patent 5,445,313 of Boyd et al., United States Patent 5,467,913 of Nemekawa et al., United States Patent 5,615,823 of Noda et al., United States Patent 5,680,984 of Sakemi, United States Patent 5,685,477 of Mallik et al., United States Patent 5,687,901 of Hoshiba et al., and United States Patent 5,695,667 of Eguchi et al. In each of these publications, release of the array of solder balls onto contacts of a substrate is accomplished by shutting off the vacuum.

United States Patent 5,506,385 of Murakami et al. discloses the use of a single manipulable suction head for picking up a solder ball, moving it to a position above a fluxed contact pad on a substrate, and depositing it on the contact pad.

United States Patent 5,695,667 shows a single ball suction head which is used to place a solder ball on a contact pad which is missing a solder ball of a ball-grid-array.

The application of flux to solder balls held in a vacuum apparatus by dipping the balls into a flux reservoir is taught in United States Patent 5,088,639 of Gondotra et al. and in United States Patent 5,284,287 of Wilson et al.

The use of ultrasonic vibration to cause solder ball movement in the ball reservoir, and to remove excess solder balls from a vacuum pickup tool, is taught in United States Patent No. 5,687,901 of Hoshiba et al.

5

BRIEF SUMMARY OF THE INVENTION

At present, the invention is directed to methods and apparatus for handling solder balls in forming ball grid arrays (BGA's) for manufacturing reliable interconnections between a semiconductor device and a substrate.

10

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

The following drawings illustrate various embodiments of the invention, wherein:

FIG. 1 is a perspective schematic view of an exemplary apparatus illustrating the steps of forming a ball-grid-array interconnection in accordance with a method of the invention;

15

- FIG. 2 is a sectional side view of a ball pickup tool useful in a method of forming a ball-grid-array interconnection in accordance with the invention;
- FIG. 3 is a sectional side view of a ball pickup tool picking up solder balls for the formation of a ball-grid-array interconnection in accordance with a method of the invention;

20

FIG. 4 is a sectional side view of a ball pickup tool in the process of dipping into a reservoir of attachment agent to apply attachment agent to the picked up balls, in accordance with a method of the invention;

FIG. 5 is a sectional side view of a ball pickup tool following dipping into a reservoir of attachment agent, in accordance with a method of the invention;

accordance with a method of the invention;

reservoir of attachment agent, in accordance with a method of the invention;

FIG. 6 is a sectional side view of a ball pickup tool aligned with a substrate in

25

FIG. 7 is a sectional side view of a ball pickup tool placing solder balls onto the bond pads of a substrate in accordance with a method of the invention;

- FIG. 8 is a sectional side view of a substrate having a ball-grid-array formed thereon in accordance with a method of the invention;
- FIG. 9 is a generalized graphical representation of the pressure exerted on the ball seats of a ball pickup tool as a time function in a method of the invention;
- FIG. 10 is a perspective view of another embodiment of a ball pickup tool of the invention;
- FIG. 11 is a sectional side view of a substrate in a process of having a ball-grid-array formed thereon in a method of another embodiment of the invention;
- FIG. 11A is a sectional side view of a substrate in a process of having a ball-grid-array formed thereon in a method of another embodiment of the invention wherein the substrate holder includes a screen thereon;
- FIG. 12 is an enlarged view of a step in a process of forming a ball-grid-array on a substrate in accordance with another embodiment of the invention;
- FIG. 13 is an enlarged view of a step in a process of forming a ball-grid-array on a substrate in accordance with another embodiment of the invention; and
- FIG. 14 is an enlarged view of a substrate having a ball-grid-array formed thereon in accordance with an embodiment of the invention.

DETAILED DESCRIPTION OF THE INVENTION

20

25

5

10

15

The invention comprises an improved method and apparatus for forming a ball-grid-array of spherical or semi-spherical preformed solder balls on conductive sites on a surface of an electronic apparatus. The term "substrate" is used in a broad generic sense herein to include any semiconductor device including a bare die, as well as traditional substrates including circuitized boards such as printed circuit boards (PCB's). The method of the invention may be applied to the attachment of solder balls to any conductive site.

As depicted in drawing FIG. 1, a solder ball mounting apparatus 10 includes a ball pickup tool 20, also called herein a ball pickup head. The ball pickup head 20 is connected to a positioner 12 which controls the movement of the ball pickup head in three

10

15

20

25

axes. The ball pickup head 20 is controllable along X-axis 14, Y-axis 16 and Z axis 18 for alignment with a ball reservoir 30, an attachment agent reservoir 40, and a first substrate 50. The ball pickup head 20 may also be controllable about one or more axes of rotation 22, 24, 26.

The ball pickup head 20 may be as illustrated in drawing FIG. 2, comprising a body 28 with internal chamber 32. A lower plate 34 is shown with a plurality of generally hemispherical ball seats 36, each seat configured to attract and retain a single preformed solder ball 60. A passageway 38 between each seat 36 and the internal chamber 32 permits vacuum suction 42 or gas pressure to be controllably applied to the seats 36 for alternatively retaining solder balls 60 thereon or discharging solder balls therefrom. The internal pressure within the internal chamber 32 is controlled by alternate activation of vacuum valve 46 and compressed gas valve 48. The pickup head 20 may be provided with a heater 92 by which it can quickly attain a temperature at which a particular solder will reflow, typically 183 °C or greater, or heated to a sufficient level to at least provide a temporary bond between a solder ball 60 and a bond pad 72, forming a ball-grid array 62.

The pattern of ball seats 36, when inverted, is configured to match a bond pad array 72 on a substrate 50 to which the balls 60 are to be attached.

As shown in FIG. 3, a solder ball reservoir 30 is configured to hold a large number of preformed solder balls 60 and has gas sparge holes 54 for fluidizing the balls within the reservoir, whereby the balls are attracted to and held by vacuum suction in the ball seats 36. Other alternative (or additional) means for fluidizing the balls 60 may be used, such as a vibrator 62.

As depicted in drawing FIGS. 1 and 4, the solder ball mounting apparatus 10 includes an attachment agent reservoir 40 containing an attachment agent 70. The attachment agent 70 may be a flux of conventional or other composition and, in an embodiment of the invention, comprises a pressure sensitive adhesive (PSA) which melts when heated.

The invention encompasses the use of the formed ball-grid-array 62 on a first substrate 50 for attachment of a second substrate 80 thereto. While the first substrate 50

is depicted as a circuit board, the second substrate 80 is shown as a semiconductor device. The first substrate 50 and/or second substrate 80 are moved and positioned by a positioner, not shown. The first substrate 50 has the solder balls 60 of the ball-grid-array 62 attached to the bond pads 72 on the substrate 50 by the reflow heating of the substrate 50 in a furnace. The first and second substrates 50, 80 are then adjoined and heated to a reflow temperature wherein the solder balls 60 flow to adhere to the bond pads 72 on the first substrate and bond pads 82 on the second substrate. The heating may take place in a reflow furnace 90, for example, and subsequent cooling results in a high quality electrical interconnection between the two substrates.

10

5

Using this apparatus 10, several different methods may be used for attaching preformed solder balls 60 to a substrate 50. In a first method, illustrated in drawing FIGS. 3-9, a ball pickup head 20 is lowered by movement 64 into the bed of fluidized solder balls 60 in reservoir 30. (See drawing FIG. 3.) The vacuum valve 46 is then opened to provide suction to the ball seats 36, which quickly become filled with solder balls 60. The pickup head 20 is then retracted from the ball reservoir 30 and positioned over an attachment agent reservoir 40 by movement 66. As shown in drawing FIG. 4, the pickup head 20 with a solder ball 60 held in each ball seat 36 is then lowered by movement 68 into the attachment agent reservoir 40 so that each solder ball 60 is slightly submerged in the surface 84 of attachment agent 70. A sub-atmospheric pressure is maintained on each solder ball 60 to hold it in its seat 36.

20

15

The attachment agent 70 is any material which permits or enhances attachment of a solder ball 60 to a bond pad 72, and temporarily holds a solder ball on the bond pad until it may be bonded by reflow thereto. Fluxes of various types are commonly used as attachment agents 70. As particularly taught in this application, a pressure sensitive adhesive (PSA) may also be used as the attachment agent 70. Pressure sensitive adhesives such as those formed of epoxy, or other suitable known adhesives, may be used.

25

The ball pickup head 20 is retracted from the attachment agent reservoir 40 and positioned over a bond pad array 72 of a first substrate 50 by movement 74. As depicted

10

15

20

25

in drawing FIG. 5, each solder ball 60 held in a ball seat 36 of the pickup head 20 is shown with a small quantity of attachment agent 70 on its lower surface.

In an alternative embodiment of the method, the attachment agent 70 is directly applied to the bond pads 72 rather than applied to the balls 60 by dipping or wiping. The step of applying attachment agent 70 to the solder balls 60 as shown in drawing FIGS. 4 and 5 is then deleted.

As depicted in drawing FIGS. 6 and 7, the ball pickup head 20 with held solder balls 60 is lowered by movement 76 until the balls 60 are just above the bond pads 72, or the attachment agent 70 just touches the bond pads. Preferably, at this time, the pickup head 20 is moved slightly in a lateral direction 88 whereby each ball wipes the attachment agent 70 over the bond pad surface to enhance subsequent bonding. The optimum vertical position is dependent on several factors including ball size, bond pad size, type and quantity of attachment agent 70, etc. and may be found by a process of trial and error.

As shown in drawing FIG. 7, the vacuum valve 46 is shut off and the compressed gas valve 48 is opened for a brief time, and the "puff" of pressure ejects the balls 60 onto the bond pads 72. The small quantity of attachment agent 70 holds each ball 60 in a generally central portion of its bond pad 72. Each ball 60 moves a very small distance, but the movement is sufficient to permit gas flow 86 from chamber 32 to escape past the ball. Alternatively, the pickup head may be vibrated a very small amplitude to achieve the same result.

At this point, the method of the invention may take one of several alternative steps.

First, the heater 92 may be used to provide a full reflow temperature to fully bond the solder balls 60 to the bond pads 72.

Second, the ball pickup head 20 may be lifted by movement 78 away from the first substrate 50, and the balls 60 bonded to the bond pads 72 by another source of heat. As depicted in drawing FIG. 8, the result is a first substrate 50 having a uniform ball-grid-array 94, ready for bonding to a second substrate 80.

Third, the ball pickup head 20 may be lifted by movement 78 from the first substrate 50 and the balls 60 bonded to the bond pads 72 by another source of heat.

Subsequently, a second substrate 80 is attached to the first substrate, followed by treating at a reflow temperature, e.g. by insertion in a reflow furnace 90 or heating the substrate(s) using a block heater(s) (not shown). The result is an electronic apparatus comprising two substrates 50, 80 with a reliable BGA interconnection therebetween.

5

Illustrated in drawing FIG. 9 is the time-pressure pattern of the ball pickup head 20 in the BGA formation process. Arrow 102 indicates the point at which all ball seats 36 are filled from the ball reservoir 30. Arrow 104 indicates the onset of dipping the balls 60 into the attachment agent 70, and arrow 106 indicates withdrawal of the balls from the attachment agent reservoir 40. Arrow 108 indicates the point at which the vacuum 42 is shut off, and gas (e.g. air) pressure started, to eject the balls 60 from the ball seats 36. Arrow 110 indicates the end of the gas puff when the gas 44 is shut off. The gas puff is short in duration, generally shorter than 3 seconds, and it may be less than 0.5 seconds.

As shown in drawing FIG. 10, the ball pickup head or tool 20 may be configured

15

10

20

to manipulate a single solder ball 60. While many variations in the construction are possible, the pickup head 20 is generally depicted as having a body 28 from which a hollow vacuum/pressure tip 96 extends outwardly and downwardly for holding and moving a solder ball 60 in a ball seat 36 at its distal end 98. The vacuum/pressure tip 96 is connected through a valve 46 to a vacuum source 42 for attracting and holding a solder ball 60. Valves 46 and 48 may be solenoid actuated valves. The tip 96 is also connected through a valve 48 to a compressed gas (such as air) source 44. The airflow may be controlled to provide a brief puff of pressure to the seated ball 60 to eject it from the ball seat 36 onto the surface of a bond pad, as previously described. The vacuum/pressure tip 96 may be lowered into a ball reservoir 30 and/or an attachment agent reservoir 40, as

25

In one embodiment of the single ball pickup head 20, a ball feeder 112 comprises a solder ball vessel 114 and a tubular ramp 116 leading from the vessel 114 to a position adjacent the ball seat 36 when the vacuum/pressure tip 96 is retracted upwardly. A valve 118 releases one ball 60 at a time, and may comprise a pin valve operated by a solenoid. Other types of valves 118 known in the art may be used.

previously shown in drawing FIGS. 1-4.

10

15

20

25

A gas flow from a gas source 120 may be introduced into the ball vessel 114 near the ramp 116 to ensure uninterrupted ball flow in the ramp 116.

The ball feeder 112 is preferably maintained at a constant elevation, so that the ball pickup head 20 is retracted upwardly from a lower level to pick up a new ball 60.

The ball pickup head 20, whether of a single ball configuration or a multiple ball configuration, is connected to a positioner (not shown) by which it may be manipulated along three axes X, Y, and Z. Preferably, it may also be rotated about at least one axis. It may be incorporated in a high-speed automated machine using pattern recognition and other alignment methods, with robotic movement, and include all steps through solder reflow in an integral furnace.

Turning now to drawing FIGS. 11-14, an embodiment for forming a ball-grid-array interconnection of preformed solder balls 60 on a substrate 50 is illustrated. In drawing FIG. 11, a substrate 50 is retained in a substrate holder 122. In drawing FIG. 11A, the substrate holder 122 includes a screen 123 thereon, the screen 123 having a plurality of apertures therein corresponding to the array of bond pads 72 on the substrate 50 to assist in the location of the solder balls 60 on the bond pads 72 of a substrate 50. In any event, the substrate 50 has conductive bond sites, e.g. pads 72, on a lower surface 124, and each pad is coated or otherwise covered (at least partially) by an attachment agent 70, as shown in drawing FIG. 12. The agent 70 may comprise flux or a pressure sensitive adhesive (PSA). The method of application of attachment agent 70 to the bond pads 72 is important to the invention only to the extent that fluidized or non-fluidized solder balls 60 from a ball reservoir 30 will adhere to the agent. Thus, the attachment agent 70 may be applied by screening, dipping, direct flow or contact, etc.

As depicted, the method comprises lowering the array of bond pads 72 into a solder ball reservoir 30 in which balls 60 are fluidized by gas 56 introduced through valve 58 and passing through sparge holes 54. Alternatively or in addition to the gas sparging, a vibrator 62 may be used as shown in drawing FIG. 3. A solder ball 60 becomes directly attached to each bond pad 72 (See drawing FIG. 13). The substrate 50

10

15

20

25

may then be inverted as shown in drawing FIG. 14 and heated to bond the balls 60 to the bond pads 72. The substrate 50 is then ready for bonding to another substrate.

This method is very simple when compared to prior art methods of forming ball-grid-arrays. No alignment of the substrate is required for ball attachment. Alternately, if desired, a screen may be used on the substrate holder 122 to locate the solder balls on the bond pads on the substrate. No solder balls are wasted. The result is a BGA interconnection formed at very low cost.

Some variation in alignment of balls 60 on the bond pads 72 may occur, but will not affect the performance. As shown in drawing FIG. 13, the offset 130 between the bond pad centerline 132 and the ball centerline 134 is generally so small as to not be a problem. In a preferred embodiment, the bond pad side dimension 126 is minimized relative to the ball diameter 128. Preferably, the side dimension 126 does not exceed the ball diameter 128. More preferably, the side dimension 126 is not more than one-half of the ball diameter 128, i.e. does not exceed the overall ball radius. Thus, the attachment of more than one ball 60 to a bond pad 72 is generally precluded.

In addition, the bond pads 82 of a second substrate 80 to be attached to the first substrate 50 are made larger than bond pads 72. Thus, no problem is encountered in achieving a reliable BGA interconnection between the two substrates 50, 80.

The methods described herein present many advantages to the BGA formation process, including higher reliability, lower cost, reduced ball wastage, etc.

This invention may be embodied in several forms without departing from the spirit of essential characteristics of the invention. The embodiments as described herein are therefore intended to be only illustrative and not restrictive, and the scope of the invention is defined by the appended claims rather than the preceding description, and all variations that fall within the metes and bounds of the subject matter claimed, or are equivalent thereto, are therefore intended to be embraced by the following claims.

10

15

20

25

CLAIMS

What is claimed is:

source;

- A tool for placing preformed solder balls on a substrate, comprising:
 a tool body controllably movable in multiple axes and rotatable about an axis;
 a plurality of ball seats formed in said body for said preformed solder balls, said plurality of ball seats each having an aperture therein;
 a passageway leading from said aperture to a vacuum source and to a pressurized gas
- valve apparatus for controlling separately and independently a vacuum and a gas under pressure to said ball seats, said vacuum retaining said solder balls on said ball seats, and said pressurized gas releasing said solder balls from said ball seats.
- 2. The pickup tool of claim 1, wherein said vacuum holds said solder balls in said ball seats and said pressurized gas ejects said solder balls from said ball seats.
- 3. The pickup tool of claim 1, wherein said vacuum holds said solder balls in said ball seats and said pressurized gas ejects said solder balls from said ball seats to a plurality of bond pads on said substrate.
- 4. The pickup tool of claim 1, further comprising:
 a controllable ball dispenser supplying solder balls to said pickup tool, comprising:
 a ramp for feeding solder balls to said ball seats, said ramp having an upper end and a lower end;
- a controllable valve at the lower end of said ramp for releasing a single solder ball of said solder balls on demand to said ball seats using a vacuum applied to said ball seats; and
- a reservoir providing a supply of solder balls to said ramp.

| | 5. | The pickup tool of claim 4, further comprising: |
|------|--------------|--|
| a ga | s inlet in s | said reservoir, said gas inlet connected to a source of pressurized gas for |
| | provid | ling gas flow through said solder balls to provide a non-interrupted flow of |
| | said so | older balls through said ramp. |

6. The pickup tool of claim 4, wherein said ramp holds a series of solder balls having a diameter in the range of about 0.01 mm to about 0.15 mm.

10

7. The pickup tool of claim 1, further comprising:
a screen having a plurality of apertures therein, an aperture of said plurality of apertures located adjacent an aperture of said ball seats formed in said body for said solder balls.

15

- 8. A pickup tool for placing a plurality of solder balls on ball-grid-array bond pads of a substrate, said pickup tool comprising:
- a pickup tool body with a hollow chamber therein;
- a lower plate having a plurality of seats therein for retaining a solder ball in each seat, said plurality of seats corresponding to an inverted configuration of an array of bond pads on a substrate;

20

- a plurality of passageways leading from each said seat to said hollow chamber;
- a passageway leading from said chamber to a vacuum source;
- a passageway leading from said chamber to a pressurized gas; and
- controllable valve apparatus for controlling opening and closing said vacuum passageway and pressurized gas.

25

- 9. The pickup tool of claim 8, further comprising:
- a heater to heat said pickup to a temperature to bond said solder balls bond to said bond pads of said substrate.

| # 1 | |
|---|--|
| z: | |
| 2 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 | |
| Ĩ | |
| THE STATE | |
| ÷ | |
| z? | |
| | |
| Ü | |
| 7 | |
| | |
| <u>.</u> 3 | |
| 2 | |
| ż | |
| an. | |

10. A pickup tool for placing preformed solder balls on a substrate, comprising:
a tool body controllably movable in multiple axes and rotatable about an axis;
a plurality of ball seats formed in said tool body for a plurality of solder balls, each ball seat of said plurality of ball seats having an aperture therein;
a passageway leading from said aperture to a vacuum source and to a pressurized gas; and controllable valve apparatus controlling the vacuum and the pressurized gas to said ball seat, said vacuum retaining said solder ball in each said ball seat and said pressurized gas

10

5

11. The pickup tool of claim 10, wherein said vacuum holds said solder ball in said ball seat and said pressurized gas ejects said solder ball from said ball seat to a bond pad on a substrate.

releasing solder ball from said ball seat.

15

12. The pickup tool of claim 10, further comprising:
a solder ball dispenser supplying solder balls to said pickup tool, comprising:
a tubular ramp for feeding solder balls to said ball seat, said ramp having an upper end and a lower end;
a controllable valve at the lower end of said ramp for releasing a single solder ball to said ball seat while a vacuum is applied to said ball seat;
a reservoir for providing a supply of solder balls to move downwardly through said ramp.

20

13. The pickup tool of claim 12, further comprising: a gas inlet in said reservoir, said gas inlet connected to said pressurized gas providing gas flow through said solder balls providing a non-interrupted flow of solder balls through said ramp.

25

14. The pickup tool of claim 12, wherein said ramp holds solder balls having a diameter of about 0.01 mm to about 0.15 mm.

10

substrate.

- 15. A pickup tool for placing a plurality of solder balls on ball-grid-array bond pads of a substrate, said pickup tool comprising:
- a pickup tool body with a hollow chamber therein;
- a lower plate having a plurality of seats therein for attracting and retaining a solder ball in each seat, said plurality of seats corresponding to an inverted array of bond pads on a substrate;

passageways leading from each said seat of said plurality of seats to said hollow chamber; a passageway leading from said chamber to a vacuum source;

- a passageway leading from said chamber to a pressurized gas; and controllable valve apparatus controllably said vacuum and pressurized gas.
- 16. The pickup tool of claim 15, further comprising:
 a heater to heat said solder balls to a temperature to bond to said bond pads on said


ABSTRACT OF THE DISCLOSURE

An array of solder balls is formed on a first substrate for interconnecting with conductive sites on another substrate. A ball pickup tool picks up balls with a vacuum suction from a fluidized ball reservoir and utilizes a puff of gas to release the solder ball(s) carried thereon to conductive sites of a substrate for bonding thereto. In another embodiment, the bond pads of a substrate are coated with a flux or adhesive and lowered into a fluidized ball reservoir for direct attachment of solder balls.

10

5

N·\2269\3636 1\div.pat.app.wpd 8/14/00






FIG. 2




FIG. 3





FIG. 4






FIG. 6




FIG. 7






FIG. 8



F1G. 9







FIG.







FIG. 12






FIG. 14

DECLARA ... N FOR PATENT APPLICATION (WITH POWER OF ... TORNEY)

As an inventor named below or on any attached continuation page, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name.

I believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled METHOD OF ATTACHING SOLDER BALLS TO BGA PACKAGE UTILIZING A TOOL TO PICK AND DIP THE SOLDER BALL IN FLUX, the specification of which (check one):

| | | was amended on | | |
|--|--|--|--|--|
| □ was filed onas l | | as amended under PCT Article 19 on | · | |
| I hereby state that I have reviewed referred to above. | and understand the contents of the above-identified | specification, including the claims, as amen | ided by any an | nendment |
| I acknowledge the duty to disclose matter claimed in this application, as | to the U.S. Patent and Trademark Office all inform 'materiality" is defined in Title 37, Code of Federal | ation known to me to be material to the pate Regulations § 1.56. | entability of th | e subject |
| attached continuation page and have al | efits under Title 35, United States Code, § 119(a)-(ernational application(s) designating at least one counts of identified below and on any attached continuation esignating at least one country other than the United med. | atry other than the United States of America | listed below | |
| Prior foreign/PCT application(s): | | | Priority C | Toimed |
| (number) | (country) | (day/month/year filed) | Yes | No |
| (number) | (country) | (day/month/year filed) | Yes | No |
| application is not disclosed in any such | tle 35, United States Code, § 120 of any United States listed below and on any attached continuation page prior application in the manner provided by the first and Tradescale Office William | e and, insofar as the subject matter of each | of the claims | of this |
| application is not disclosed in any such the duty to disclose to the U.S. Patent a Regulations § 1.56 which became avail | prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application. | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing | of the claims e, § 112, I ack Title 37, Code g date of this | of this |
| application is not disclosed in any such the duty to disclose to the U.S. Patent Regulations § 1.56 which became avail | ca listed below and on any attached continuation page prior application in the manner provided by the first and Trademark Office all information known to me | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in | of the claims e, § 112, I ack Title 37, Code g date of this | of this |
| application is not disclosed in any such the duty to disclose to the U.S. Patent a Regulations § 1.56 which became avail (application serial no.) | ca listed below and on any attached continuation pag prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application (filing date) | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) | of this nowledge e of Feder application |
| application is not disclosed in any such the duty to disclose to the U.S. Patent a Regulations § 1.56 which became avail (application serial no.) | railisted below and on any attached continuation page prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application (filing date) | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) | of this nowledge e of Feder application |
| application is not disclosed in any such the duty to disclose to the U.S. Patent a Regulations § 1.56 which became avail (application serial no.) | ca listed below and on any attached continuation pag prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application (filing date) | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) | of this nowledge e of Feder application |
| designating the Officer States of Americapplication is not disclosed in any such the duty to disclose to the U.S. Patent a Regulations § 1.56 which became avail (application serial no.) (application serial no.) I hereby claim the | ca listed below and on any attached continuation pag prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application (filing date) (filing date) e benefit under Title 35, United States Code, § 1196 | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) | of this nowledge e of Feder application |
| (application serial no.) (application serial no.) (application serial no.) I hereby claim the (provisional application no.) | ca listed below and on any attached continuation pag prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application (filing date) (filing date) e benefit under Title 35, United States Code, § 119(| e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) | of this nowledge e of Feder application |
| application is not disclosed in any such the duty to disclose to the U.S. Patent and Regulations § 1.56 which became avail (application serial no.) (application serial no.) I hereby claim the (provisional application no.) (provisional application no.) | ca listed below and on any attached continuation pag prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior applicatio (filing date) (filing date) (filing date) (filing date) (filing date) | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a se) of any United States provisional applications. | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) abandoned) ion(s) listed be | of this nowledge of Feder application |
| application is not disclosed in any such the duty to disclose to the U.S. Patent and the duty to disclose to the U.S. Patent and the duty to disclose to the U.S. Patent and the duty to disclose to the U.S. Patent and the duty to disclose to the U.S. Patent and the the U.S. Patent a | can listed below and on any attached continuation pag prior application in the manner provided by the first and Trademark Office all information known to me able between the filing date of such prior application (filing date) William S. Britt, Reg. No. 20,969 | e and, insofar as the subject matter of each t paragraph of Title 35, United States Code to be material to patentability as defined in and the national or PCT international filing (status - pending, patented or a (status - pending, patented or a se) of any United States provisional applications. | of the claims e, § 112, I ack Title 37, Code g date of this abandoned) abandoned) abandoned) ion(s) listed be ademark Office | of this nowledge of Feder application |

tr or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of first joint inventor: Inventor's signature Residence: Boise, Idaho Citizenship: U.S.A.

Post Office Address: 608 Boise Hills Drive, Boise, Idaho 83702

, <u>9/30/98</u> . <u>9/30/98</u>

DECLARATION FOR PATENT APPLICATION

(continuation page)

Invention title: METHOD OF ATTACHING SOLDER BALLS TO BGA PACKAGE UTILIZING A TOOL TO PICK AND DIP THE SOLDER BALL IN FLUX

Inventor name(s) appearing on first declaration page: Chad A. Cobbley

Additional original, first and joint inventor(s):

Full name of second joint inventor: Michael B. Ball Inventor's signature

Residence: Boise, Idaho Citizenship: U.S.A.

Post Office Address: 8630 Pembrook Drive, Boise, Idaho 83704

Jayone o

Full name of third joint investor: Marjorie L. Waddel Wa

Inventor's signature Residence: Boise, Idaho

Citizenship: U.S.A.

(,fi

ijij

Post Office Address: 7903 W. Bayhill Ct., Boise, Idaho 83704